

PVC S58-02

Description

PVC S58-02 is a low K-value polyvinyl chloride grade, manufactured by a suspension polymerisation process. It is a medium porous polymer with a high bulk density and an excellent thermal stability

Typical Values

Property	Value *	Unit	Test Method
K-value	58	-	ISO 1628-2
Bulk density	0.570	g/ml	ISO 60
Sieve Analysis			ISO 4610
> 63µm	≥ 98	%	
> 250µm	≤ 0.5	%	
Volatile content	≤ 0.3	%	ISO 1269
Plasticiser absorption	18	%	ISO 4608
Residual Vinyl Chloride	< 1	ppm	ASTM D3749

*Data obtained on representative samples of this grade. These values are typical, for guidance only and must not be used as a basis for specifications.

Applications

PVC S58-02 can either be used for injection moulding of rigid articles, such as pipe fittings; or for the production of foamed products (i.e boards, core layer foamed pipes...).

Shipping

In general, shipping of the resin is done in bulk. Most common bulk transport modes are silotricks and pressurized containers for rail and sea transport.

Storage

The resin must be stored in a dry area under moderate temperature conditions (maximum 30 °C) and avoid direct UV light exposure.

Safety

For information on the safety precautions of S58-02 please refer to our material safety datasheet (MSDS). The MSDS can be sent on request of the customer.